



Force Drying

FLASH TIME 15 MINUTES

BAKE TIME @ 140° F 40 MINUTES

Note: Allow a 1-2 hour cool-down time before wet sanding or buffing after force drying.



Physical Data

Weight Solids (RTS): 40.93%

Volume Solids (RTS): 33.04%

Coverage: 685 sq. ft. per gallon @ 1 dry mil

V.O.C. (RTS): 4.2 lbs/gal



Safety

Before using any Zolatone product be sure to read all MSDS, application instructions and warnings. Always wear a properly fitted air purifying respirator with organic cartridges and a particulate filter or a fresh air supplied respirator (depending on product selection), eye protection, gloves and protective clothing while exposed to any chemical.



Warning Statement

This product is intended for use by professionally trained painters only. Use as directed. The data presented herein was determined under our controlled conditions. Since environmental conditions play a large role in performance, variations in the data presented herein may be observed as environmental conditions change. This document does not constitute a warranty or guarantee of any kind.